1. IDENTIFICATION OF THE SU Material Name Uses		TANCE/PREPARATION AND COMPANY/UNDERTAKING Shell Advance VSX 2 Engine oil.
Product Code	:	001A9108
Manufacturer/Supplier	:	Shell India Markets Private Limited 2nd Floor, Campus 4A RMZ Millenia Park 143 Dr. MGR Road, Perungudi CHENNAI 600096 India
Telephone Fax	:	(+91) 04443450000 (+91) 04443451516
Emergency Telephone Number	:	+91 22 6516 1058

### 2. COMPOSITION/INFORMATION ON INGREDIENTS

Mixture Description

: Highly refined mineral oils, additives, kerosine or similar hydrocarbon solvent and dye.

Hazardous Comp	onents				
Chemical	CAS	EINECS	Symbol(s)	R-phrase(s)	Conc.
Identity					
Distillates	64742-47-8	265-149-8	Xn	R65; R66	10.00 - 30.00 %
(petroleum),					
hydrotreated light					

Additional Information : The highly refined mineral oil contains <3% (w/w) DMSOextract, according to IP346. Refer to chapter 16 for full text of EC R-phrases.

3. HAZARDS IDENTIFICATION		
EC Classification	:	Not classified as dangerous under EC criteria.
Health Hazards	:	Not expected to be a health hazard when used under normal conditions. Prolonged or repeated skin contact without proper cleaning can clog the pores of the skin resulting in disorders such as oil acne/folliculitis. Used oil may contain harmful impurities.
Signs and Symptoms	:	Oil acne/folliculitis signs and symptoms may include formation of black pustules and spots on the skin of exposed areas. Ingestion may result in nausea, vomiting and/or diarrhoea.
Safety Hazards Environmental Hazards	:	Not classified as flammable but will burn. Not classified as dangerous for the environment.

4. FIRST AID MEASURES	N
General Information	: Not expected to be a health hazard when used under normal
Inhalation	conditions. : No treatment necessary under normal conditions of use. If
innalation	symptoms persist, obtain medical advice.
Skin Contact	: Remove contaminated clothing. Flush exposed area with water
	and follow by washing with soap if available. If persistent
	irritation occurs, obtain medical attention.
Eye Contact	: Flush eye with copious quantities of water. If persistent
Ingestion	irritation occurs, obtain medical attention.
Ingestion	<ul> <li>In general no treatment is necessary unless large quantities are swallowed, however, get medical advice.</li> </ul>
Advice to Physician	: Treat symptomatically.
······	
5. FIRE FIGHTING MEASURES	3
Clear fire area of all non-eme	ergency personnel.
Specific Hazards	Hazardous compustion products may include A complex
ορευπις Παζαιώδ	: Hazardous combustion products may include: A complex mixture of airborne solid and liquid particulates and gases
	(smoke). Carbon monoxide. Unidentified organic and inorganic
	compounds.
Suitable Extinguishing	: Foam, water spray or fog. Dry chemical powder, carbon
Media	dioxide, sand or earth may be used for small fires only.
Unsuitable Extinguishing	: Do not use water in a jet.
Media Protective Equipment for	: Proper protective equipment including breathing apparatus
Firefighters	must be worn when approaching a fire in a confined space.
equipment see Chapter 8 of	released material. For guidance on selection of personal protective this Material Safety Data Sheet. See Chapter 13 for information on ant local and international regulations.
Protective measures	: Avoid contact with skin and eyes. Use appropriate containment
	to avoid environmental contamination. Prevent from spreading
	or entering drains, ditches or rivers by using sand, earth, or
	other appropriate barriers.
Clean Up Methods	: Slippery when spilt. Avoid accidents, clean up immediately.
	Prevent from spreading by making a barrier with sand, earth or
	other containment material. Reclaim liquid directly or in an absorbent. Soak up residue with an absorbent such as clay,
	sand or other suitable material and dispose of properly.
Additional Advice	: Local authorities should be advised if significant spillages
	cannot be contained.
. HANDLING AND STORAGE General Precautions	: Use local exhaust ventilation if there is risk of inhalation of
	vapours, mists or aerosols. Properly dispose of any
	contaminated rags or cleaning materials in order to prevent
	fires. Use the information in this data sheet as input to a risk
	assessment of local circumstances to help determine
	2/7
Print Date 22 03 2012	00000000

		appropriate controls for safe handling, storage and disposal of this material.
Handling	:	Avoid prolonged or repeated contact with skin. Avoid inhaling vapour and/or mists. When handling product in drums, safety footwear should be worn and proper handling equipment should be used.
Storage	:	Keep container tightly closed and in a cool, well-ventilated place. Use properly labelled and closeable containers. Store at ambient temperature.
Recommended Materials	:	For containers or container linings, use mild steel or high density polyethylene.
Unsuitable Materials	:	PVC.
Additional Information	:	Polyethylene containers should not be exposed to high temperatures because of possible risk of distortion.

#### 8. EXPOSURE CONTROLS/PERSONAL PROTECTION

If the American Conference of Governmental Industrial Hygienists (ACGIH) value is provided on this document, it is provided for information only.

#### **Occupational Exposure Limits**

Material	Source	Туре	ppm	mg/m3	Notation
Oil mist, mineral	IN OEL	TWA(Mist.)		5 mg/m3	
	IN OEL	STEL(Mist.)		10 mg/m3	
	ACGIH	TWA(Inhala ble fraction.)		5 mg/m3	

Exposure Controls Personal Protective Equipment	:	The level of protection and types of controls necessary will vary depending upon potential exposure conditions. Select controls based on a risk assessment of local circumstances. Appropriate measures include: Adequate ventilation to control airborne concentrations. Where material is heated, sprayed or mist formed, there is greater potential for airborne concentrations to be generated. Personal protective equipment (PPE) should meet recommended national standards. Check with PPE suppliers.
Respiratory Protection	:	No respiratory protection is ordinarily required under normal conditions of use. In accordance with good industrial hygiene practices, precautions should be taken to avoid breathing of material. If engineering controls do not maintain airborne concentrations to a level which is adequate to protect worker health, select respiratory protection equipment suitable for the specific conditions of use and meeting relevant legislation. Check with respiratory protective equipment suppliers. Where air-filtering respirators are suitable, select an appropriate combination of mask and filter. Select a filter suitable for combined particulate/organic gases and vapours [boiling point >65°C(149 °F)].

Environmental Exposure	<ul> <li>confirm compliance with an OEL and adequacy of exposure controls. For some substances biological monitoring may also be appropriate.</li> <li>Minimise release to the environment. An environmental</li> </ul>
Controls	assessment must be made to ensure compliance with local environmental legislation.
9. PHYSICAL AND CHEMICAL	
Appearance	: Amber. Liquid.
Odour	: Slight hydrocarbon.
рН	: Not applicable.
pH Initial Boiling Point and	: Not applicable.
pH Initial Boiling Point and Boiling Range	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility Solubility in other solvents	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> <li>Data not available</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility Solubility in other solvents n-octanol/water partition	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility Solubility in other solvents	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> <li>Data not available</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility Solubility in other solvents n-octanol/water partition coefficient (log Pow)	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> <li>Data not available</li> <li>&gt; 6 (based on information on similar products)</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility Solubility in other solvents n-octanol/water partition coefficient (log Pow) Dynamic viscosity	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> <li>Data not available</li> <li>&gt; 6 (based on information on similar products)</li> <li>Data not available</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility Solubility in other solvents n-octanol/water partition coefficient (log Pow) Dynamic viscosity Kinematic viscosity	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> <li>Data not available</li> <li>&gt; 6 (based on information on similar products)</li> <li>Data not available</li> <li>Typical 67 mm2/s at 40 °C / 104 °F</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility Solubility in other solvents n-octanol/water partition coefficient (log Pow) Dynamic viscosity Kinematic viscosity Vapour density (air=1)	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> <li>Data not available</li> <li>&gt; 6 (based on information on similar products)</li> <li>Data not available</li> <li>Typical 67 mm2/s at 40 °C / 104 °F</li> <li>&gt; 1 (estimated value(s))</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility Solubility in other solvents n-octanol/water partition coefficient (log Pow) Dynamic viscosity Kinematic viscosity	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> <li>Data not available</li> <li>&gt; 6 (based on information on similar products)</li> <li>Data not available</li> <li>Typical 67 mm2/s at 40 °C / 104 °F</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility Solubility in other solvents n-octanol/water partition coefficient (log Pow) Dynamic viscosity Kinematic viscosity Vapour density (air=1) Evaporation rate (nBuAc=1)	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> <li>Data not available</li> <li>&gt; 6 (based on information on similar products)</li> <li>Data not available</li> <li>Typical 67 mm2/s at 40 °C / 104 °F</li> <li>&gt; 1 (estimated value(s))</li> <li>Data not available</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility Solubility in other solvents n-octanol/water partition coefficient (log Pow) Dynamic viscosity Kinematic viscosity Vapour density (air=1) Evaporation rate (nBuAc=1)	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> <li>Data not available</li> <li>&gt; 6 (based on information on similar products)</li> <li>Data not available</li> <li>Typical 67 mm2/s at 40 °C / 104 °F</li> <li>&gt; 1 (estimated value(s))</li> <li>Data not available</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility Solubility in other solvents n-octanol/water partition coefficient (log Pow) Dynamic viscosity Kinematic viscosity Vapour density (air=1) Evaporation rate (nBuAc=1) <b>10. STABILITY AND REACTIVIT</b> Stability	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> <li>Data not available</li> <li>&gt; 6 (based on information on similar products)</li> <li>Data not available</li> <li>Typical 67 mm2/s at 40 °C / 104 °F</li> <li>&gt; 1 (estimated value(s))</li> <li>Data not available</li> <li>Typical 67 mm2/s at 40 °C / 104 °F</li> <li>&gt; 1 (estimated value(s))</li> <li>Typical not available</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility Solubility in other solvents n-octanol/water partition coefficient (log Pow) Dynamic viscosity Kinematic viscosity Vapour density (air=1) Evaporation rate (nBuAc=1)	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> <li>Data not available</li> <li>&gt; 6 (based on information on similar products)</li> <li>Data not available</li> <li>Typical 67 mm2/s at 40 °C / 104 °F</li> <li>&gt; 1 (estimated value(s))</li> <li>Data not available</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility Solubility in other solvents n-octanol/water partition coefficient (log Pow) Dynamic viscosity Kinematic viscosity Vapour density (air=1) Evaporation rate (nBuAc=1) <b>10. STABILITY AND REACTIVITY</b> Stability Conditions to Avoid	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> <li>Data not available</li> <li>&gt; 6 (based on information on similar products)</li> <li>Data not available</li> <li>Typical 67 mm2/s at 40 °C / 104 °F</li> <li>&gt; 1 (estimated value(s))</li> <li>Data not available</li> <li>Stable.</li> <li>Extremes of temperature and direct sunlight.</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility Solubility in other solvents n-octanol/water partition coefficient (log Pow) Dynamic viscosity Kinematic viscosity Vapour density (air=1) Evaporation rate (nBuAc=1) <b>10. STABILITY AND REACTIVIT</b> Stability Conditions to Avoid Materials to Avoid	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> <li>Data not available</li> <li>&gt; 6 (based on information on similar products)</li> <li>Data not available</li> <li>Typical 67 mm2/s at 40 °C / 104 °F</li> <li>&gt; 1 (estimated value(s))</li> <li>Data not available</li> <li>Stable.</li> <li>Extremes of temperature and direct sunlight.</li> <li>Strong oxidising agents.</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility Solubility in other solvents n-octanol/water partition coefficient (log Pow) Dynamic viscosity Kinematic viscosity Vapour density (air=1) Evaporation rate (nBuAc=1) <b>10. STABILITY AND REACTIVIT</b> Stability Conditions to Avoid Materials to Avoid Hazardous	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> <li>Data not available</li> <li>&gt; 6 (based on information on similar products)</li> <li>Data not available</li> <li>Typical 67 mm2/s at 40 °C / 104 °F</li> <li>&gt; 1 (estimated value(s))</li> <li>Data not available</li> <li>Stable.</li> <li>Extremes of temperature and direct sunlight.</li> <li>Strong oxidising agents.</li> <li>Hazardous decomposition products are not expected to form</li> </ul>
pH Initial Boiling Point and Boiling Range Pour point Flash point Upper / lower Flammability or Explosion limits Auto-ignition temperature Vapour pressure Density Water solubility Solubility in other solvents n-octanol/water partition coefficient (log Pow) Dynamic viscosity Kinematic viscosity Vapour density (air=1) Evaporation rate (nBuAc=1) <b>10. STABILITY AND REACTIVIT</b> Stability Conditions to Avoid Materials to Avoid	<ul> <li>Not applicable.</li> <li>&gt; 280 °C / 536 °F estimated value(s)</li> <li>Typical 20 °C / 68 °F</li> <li>Typical 132 °C / 270 °F (COC)</li> <li>Typical 1 - 10 %(V) (based on mineral oil)</li> <li>&gt; 320 °C / 608 °F</li> <li>&lt; 0.5 Pa at 20 °C / 68 °F (estimated value(s))</li> <li>Typical 863 kg/m3 at 15 °C / 59 °F</li> <li>Negligible.</li> <li>Data not available</li> <li>&gt; 6 (based on information on similar products)</li> <li>Data not available</li> <li>Typical 67 mm2/s at 40 °C / 104 °F</li> <li>&gt; 1 (estimated value(s))</li> <li>Data not available</li> <li>Stable.</li> <li>Extremes of temperature and direct sunlight.</li> <li>Strong oxidising agents.</li> </ul>

Basis for Assessment	: Information given is based on data on the components and the toxicology of similar products.
Acute Oral Toxicity	: Expected to be of low toxicity: LD50 > 5000 mg/kg , Rat
Acute Dermal Toxicity	: Expected to be of low toxicity: LD50 > 5000 mg/kg , Rabbit
Acute Inhalation Toxicity	: Not considered to be an inhalation hazard under normal conditions of use.
Skin Irritation	: Expected to be slightly irritating. Prolonged or repeated skin contact without proper cleaning can clog the pores of the skin resulting in disorders such as oil acne/folliculitis.
Eye Irritation	: Expected to be slightly irritating.
Respiratory Irritation	: Inhalation of vapours or mists may cause irritation.
Sensitisation	: Not expected to be a skin sensitiser.
Repeated Dose Toxicity	: Not expected to be a hazard.
Mutagenicity	: Not considered a mutagenic hazard.
Carcinogenicity	: Product contains mineral oils of types shown to be non- carcinogenic in animal skin-painting studies. Highly refined mineral oils are not classified as carcinogenic by the International Agency for Research on Cancer (IARC). Other components are not known to be associated with carcinogenic effects.
Reproductive and Developmental Toxicity	: Not expected to be a hazard.
Additional Information	: Used oils may contain harmful impurities that have accumulated during use. The concentration of such impurities will depend on use and they may present risks to health and the environment on disposal. ALL used oil should be handled with caution and skin contact avoided as far as possible. Continuous contact with used engine oils has caused skin cancer in animal tests.

#### 12. ECOLOGICAL INFORMATION

Ecotoxicological data have not been determined specifically for this product. Information given is based on a knowledge of the components and the ecotoxicology of similar products.

Acute Toxicity	:	Poorly soluble mixture. May cause physical fouling of aquatic organisms. Expected to be practically non toxic: LL/EL/IL50 > 100 mg/l (to aquatic organisms) LL/EL50 expressed as the nominal amount of product required to prepare aqueous test extract. Mineral oil is not expected to cause any chronic effects to aquatic organisms at concentrations less than 1 mg/l.
Microorganisms	:	Data not available
Mobility	:	Liquid under most environmental conditions. Floats on water. If it enters soil, it will adsorb to soil particles and will not be mobile.
Persistence/degradability	:	Expected to be not readily biodegradable. Major constituents are expected to be inherently biodegradable, but the product contains components that may persist in the environment.
Bioaccumulation	:	Contains components with the potential to bioaccumulate.
Other Adverse Effects	:	Product is a mixture of non-volatile components, which are not expected to be released to air in any significant quantities. Not

expected to have ozone depletion potential, photochemical ozone creation potential or global warming potential.

13. DISPOSAL CONSIDERATIONS	
Material Disposal :	Recover or recycle if possible. It is the responsibility of the waste generator to determine the toxicity and physical properties of the material generated to determine the proper waste classification and disposal methods in compliance with applicable regulations. Do not dispose into the environment, in drains or in water courses.
Container Disposal :	Dispose in accordance with prevailing regulations, preferably to a recognised collector or contractor. The competence of the collector or contractor should be established beforehand.
Local Legislation	Disposal should be in accordance with applicable regional, national, and local laws and regulations.

## 14. TRANSPORT INFORMATION

#### Land (as per ADR classification): Not regulated

This material is not classified as dangerous under ADR regulations.

#### IMDG

This material is not classified as dangerous under IMDG regulations.

#### IATA (Country variations may apply)

This material is either not classified as dangerous under IATA regulations or needs to follow country specific requirements.

#### **15. REGULATORY INFORMATION**

The regulatory information is not intended to be comprehensive. Other regulations may apply to this material.

EC Classification EC Symbols EC Risk Phrases EC Safety Phrases	:	Not classified as dangerous under EC criteria. No Hazard Symbol required Not classified. Not classified.
Chemical Inventory Status		A11
EINECS	:	All components listed.
TSCA	:	All components listed.
Other Information	:	The Manufacture, Storage and Import of Hazardous Chemicals Rules 1989 (amended version issued 2000). The Factories Act, 1948, The Second Schedule: Permissible levels of certain chemical substances in work environment, as amended through 1987. India Central motor Vehicles (Amendment) Rules 1993.

#### **16. OTHER INFORMATION**

R-phrase(s)

R65 R66	Not classified. Harmful: may cause lung damage if swallowed. Repeated exposure may cause skin dryness or cracking.		
MSDS Version	Number	:	1.2
MSDS Effective	e Date	:	22.03.2012
MSDS Revision	ns	:	A vertical bar () in the left margin indicates an amendment from the previous version.
MSDS Distribu	tion	:	The information in this document should be made available to all who may handle the product.
Disclaimer		:	This information is based on our current knowledge and is intended to describe the product for the purposes of health, safety and environmental requirements only. It should not therefore be construed as guaranteeing any specific property of the product.